

TECHNICAL DATA

MECHANICAL PROPERTIES TABLE



MATERIAL PROPERTIES ACCORDING TO EN

EN GRADE	PROOF STRENGTHH		TENSILE STRENGTH R CM	ELONGATION A MIN (%)		IMP. PROPERTIES MIN. AVERAGE ABSORV. ENERGY KV		
	RP 0,2 MIN MPA	RP 1,0 MIN MPA		MPA	L	T	AT RT	
			L				T	
1.4307	180	215	470-670	40	35	100	60	60
1.4306	180	215	460-680	40	35	100	60	60
1.4311	270	305	550-760	35	30	100	60	60
1.4301	195	230	500-700	40	35	100	60	60
1.4541	200	235	500-730	35	30	100	60	60
1.4550	205	240	510-740	35	30	100	60	60
1.4404	190	225	490-690	40	30	100	60	60
1.4401	205	240	510-710	40	30	100	60	60
1.4571	210	245	500-730	35	30	100	60	60
1.4432	190	225	490-690	40	30	100	60	60
1.4429	295	330	580-800	35	30	100	60	60
1.4436	205	240	510-710	40	30	100	60	60
1.4435	190	225	490-690	40	30	100	60	60
1.4439	285	315	580-800	35	30	100	60	60
1.4438	220	250	490-690	35	30	100	60	60
1.4438	220	250	490-690	35	30	100	60	60
1.4563	215	245	500-750	40	35	120	90	60
1.4539	220	250	520-720	35	30	120	90	60
1.4547	300	340	650-850	35	30	100	60	60
1.4529	300	340	600-800	40	40	120	90	60

MATERIAL PROPERTIES ACCORDING TO ASTM

ASTM GRADE	RP 0,2 MIN MPA MIN	RP 1,0 MIN MPA MIN	TENSILE STRENGTH N/MM2	ELOGATION LO = 2" T A MIN (%)
S31500	440	-	630	30
S31500	440	-	630	30
S32900	485	-	620	20
S31803	450	-	620	25
304	205	-	515	35
304L	170	-	485	35
304LN	205	-	515	35
316	205	-	515	35
316L	170	-	485	35
316LN	300	-	650	35
317L	205	-	515	35
N08904	220	-	490	35
321	205	-	515	35
347	205	-	515	35
310	205	-	515	35